

11/24/00  
JC929 U.S. PTO  
09/18/369

BROBECK  
PHLEGER &  
HARRISON  
LLP  
ATTORNEYS AT LAW

INTELLECTUAL PROPERTY DEPARTMENT  
1333 H STREET, N.W.  
SUITE 800  
WASHINGTON  
D.C. 20005

PHONE: (202) 220-6000  
FAX: (202) 220-5200

November 24, 2000

UTILITY PATENT APPLICATION TRANSMITTAL

Attorney Docket Number: 031683.0003

First Named Inventor: Hans G. KLOTZ

Title: PROCESS AND APPARATUS FOR THE CONTINUOUS REFINING OF  
LITHARGE

TO: BOX PATENT APPLICATION  
Commissioner for Patents  
Washington, D.C. 20231

Sir:

Attached are the following for filing with the U.S. Patent and Trademark Office:

1. ☐ Fee Transmittal Form (original and duplicate)
2. ☒ Specification - Total Pages: 14 (Including Abstract)

| CLAIMS AS FILED                                 |                 |                     |       |              |              |         |
|---|-----------------|---------------------|-------|--------------|--------------|---------|
|   | Claims<br>Filed | Basic Fee<br>Claims | Extra | Rate         |              | Amount  |
|   |                 |                     |       | Large Entity | Small Entity |         |
| Total Claims                                    | 14              | 20                  | 0     | \$ 18.00     | \$ 9.00      | \$ 0.00 |
| Independent Claims                              | 2               | 3                   | 0     | \$ 80.00     | \$ 40.00     | \$ 0.00 |
| First Presentation of Multiple Dependent Claims |                 |                     |       | \$ 270.00    | \$ 135.00    | \$ 0.00 |
| BASIC FEE                                       |                 |                     |       | \$ 710.00    | \$ 355.00    | \$ 0.00 |
| TOTAL FILING FEE                                |                 |                     |       |              |              | \$ 0.00 |


3. ☒ Drawings - Total Sheets: 1 (Fig(s). 1)
4. Oath or Declaration - Total Pages: 3
  - a. ☐ Newly executed (original or copy)  
☒ New (unexecuted)
  - b. ☐ Copy from a prior application  
(for continuation/divisional with Box 17 completed)

- i. ☐ **DELETION OF INVENTOR(s):**  
Signed statement attached deleting inventor(s) named in prior application.

5. ☐ **Incorporation By Reference (useable if Box 4b is marked)**  
The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b, is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein.
6. ☐ **Microfiche Computer Program (Appendix)**
7. ☐ **Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary)**
- a. ☐ **Computer Readable Copy**
- b. ☐ **Paper Copy (identical to computer copy)**
- c. ☐ **Statement verifying identity of above copies**
8. ☐ **Assignment and Assignment Recordation Form**
9. ☐ **37 C.F.R. 3.73(b) Statement** ☐ **Power of Attorney**
10. ☐ **English Translation Document (if applicable)**
11. ☐ **Information Disclosure Statement with PTO-1449 and References**
- ☐ **Copies of Information Disclosure Statement Citations**
12. ☐ **Preliminary Amendment**
13. ☒ **Return Receipt Postcard**
14. ☐ **Small Entity Status Claimed:** ☐ **Independent Inventor**  
☐ **Small Business Concern**  
☐ **Non-Profit Organization**
- ☐ **Statement Enclosed**
- ☐ **Statement Filed in Prior Application; Status Still Proper and Desired**
15. ☐ **Foreign Priority is Claimed as Follows:**  

---

---
- ☐ **If Foreign Priority is Claimed, Certified Copy of the Above Priority Document(s) is Submitted Herewith**



**BOX PATENT APPLICATION**

November 24, 2000

Page 3

16. ☐ Other: \_\_\_\_\_
17. ☐ Continuation ☐ Divisional ☐ Continuation-in-Part of  
Prior Application No.: \_\_\_\_\_ filed \_\_\_\_\_
- ☐ Complete Application Based on Provisional Application No.: \_\_\_\_\_  
filed \_\_\_\_\_
18. ☐ A new power of attorney or authorization of agent (PTO/SB/81) is as follows:
- ☐ The power of attorney is to: Rodger L. Tate, Reg. No. 27,399; Anthony W. Shaw, Reg. No. 30,104; James Remenick, Reg. No. 36,902; Cono A. Carrano, Reg. No. 39,623; Michael J. Songer, Reg. No. 39,841; Laurence H. Posorske, Reg. No. 34,698; Floyd B. Chapman, Reg. No. 40,555; David J. Kulik, Reg. No. 36,576; Robert A. King, Reg. No. 42,738 and Trevor Q. Coddington, Reg. No. 46,633.
19. Please address all correspondence to:
- ☒ **CUSTOMER NUMBER** 26118
- ☐ Intellectual Property Department  
Brobeck, Phleger & Harrison LLP  
1333 H Street, N.W.  
Suite 800  
Washington, DC 20005
20. ☐ A check in the amount of \$ \_\_\_\_\_ is enclosed. In the event any variance exists between the amount enclosed and the Patent Office charges, please charge or credit any such variance to **Deposit Account No. 50-1640**.
- ☐ The Commissioner is hereby authorized to charge any variance between the amount enclosed and the Patent Office charges to **Deposit Account No. 50-1640**.

Respectfully submitted,

By: 

Laurence H. Posorske  
Registration No. 34,698

LHP/nej  
Enclosure

## PROCESS AND APPARATUS FOR THE CONTINUOUS REFINING OF LITHARGE

### Background of the Invention

5

The invention relates generally to the manufacture of ortho-rhombic litharge (yellow lead oxide) and in particular to a process for the continuous refining of litharge and a loopreactor for the refining of litharge.

10

Litharge is an important article of commerce, used on a large scale in a number of industrial manufacturing processes. High purity litharge, for example containing less than 0.01 % metallic lead, is typically required.

15

Litharge of sufficiently high purity for use in the glass industry has been manufactured by the Barton pot process for many years. In this process, lead is molten and fed to the Barton pot where it is agitated and contacted with air at a temperature up to 600°C. In the Barton pot, the pool of molten lead is stirred by high speed blades. This throws up droplets which are oxidized by the air, but the oxidation is incomplete. The solid powder product, containing from about 70 to 99 % PbO, is entrained in the air stream while the heavier lead droplets fall back into the pool.

20

The Barton pot process is limited by the requirement for multiple steps, involving an expensive train of equipment, and also by the fact that the maximum size of a Barton pot is limited, which frequently creates the need for a number of Barton pots to achieve a desired production level. The Barton pot process and other prior art processes are described in „LEAD OXIDES - Chemistry - Technology - Battery Manufacturing Uses - History,, (1974), Independent Battery Manufactures Association, Inc., Florida USA, at pages 21 to 25. Reference is made to Barton's US Patents 988,963 (1911) and 1,060,153 (1913), Pope and Barton USA Patent 633,533 (1899), Mayer 2,235,487 (1941), and Vehernkamp et al. 3,322,496 (1967).

30

In describing a „fused litharge furnace,, with reference to Hughes US Patent 975,955 (1910) and Petraeus US patent 592,594 (1897), which is said to be „now mainly of historical interest,, this book comments that „A mixed bath of lead

and litharge at about 1000°C has almost fantastic corrosive and erosive properties,, which has caused major problems.

The book also describes the „fume type process,, which produced a „smoke,, from which a product of fine particle size was recovered in a baghouse.  
5 (Calbeck US Patent 1,511,215 (1924) and Garesche US Patent 2,065,218 (1936)).

US Patent 3,648,936 relates to a constant acceleration fluid energy mill. Said fluid energy mill is comprising a lower inlet section and an upper classification section connected by a vertical upstack on one side and a vertical downstack on the other side, the inlet section having tangential nozzles connected to  
10 a source of gaseous fluid pressure and a raw feed inlet, whereby the raw feed particles are entrained and centrifugally whirled around the mill by the pressure fluid. The portion of the inlet chamber adjacent the upstack, as well as the upstack itself and the portion of the classification chamber adjacent the upstack form part of an antifriction curve. The classification section is preferably generally circular and  
15 has at least one exhaust outlet in the center so that the lighter particles on the inner periphery of the centrifugal path are rotated in a helical path until exhausted through the outlet. Preferably, nozzles are provided in the classification section to project pressure fluid thereinto in a generally elliptical path.

However, in view of the high density of litharge the direct adaption of  
20 said fluid energy mill for the refining of litharge is impossible. One of the important problems in the technology of refining litharge is the dosage of litharge to provide a constant flow in a continuous reactor.

### Summary of the Invention

25

The primary object of the present invention is to provide a process for the refining of litharge.

Another object of the invention is to provide a loopreactor.

Other objects and advantages of the present invention will become  
30 apparent from the following description, taken in connection with the accompanying

drawing, wherein, by way of illustration and example, an embodiment of the present invention is disclosed.

In a first embodiment the invention relates to a process for the continuous refining of ortho-rhombic litharge (yellow lead oxide) hereinafter  
5 defined as litharge, having a starting content of free metallic lead of about 1 to about 30 % by weight to litharge having a residual reduced content of free metallic lead of less than 10 % by weight, preferably less than about 1 % by weight in a reaction section 4 of a loopreactor 1, by

10 introducing a fluidized mixture of said lead containing lead oxide and a gaseous fluid into said reaction section 4 of said loopreactor 1 via an inlet section 2,

further introducing said first gaseous fluid into said reaction section 4 via a by-pass section 3, said by-pass section 3 being located in the reaction section 4 of said loopreactor 1 downstream to said inlet section 2,

15 mixing said fluidized mixture of the inlet section 2 with the gaseous fluid of the by-pass section 3 in said reaction section 4 by propelling the resultant mixture in a direction which is essentially tangential to the initial direction of said first fluidized mixture, thereby reacting the particles of lead containing lead oxide with said gaseous fluid,

20 passing said resultant, still reacting mixture through a curved path 4a, 4b in said reaction section 4, the curved path 4a, 4b being defined by a tractrix antifriction curvature (see U.S. Pat. No. 3,648,936, incorporated herein by reference) through a classification section 5 which is defined partially by a continuation of said tractrix curvature, said resultant still reacting mixture being divided into heavier  
25 particles containing a partially reduced, higher content of non-reacted metallic lead and lighter particles containing a partially reduced lower content of non-reacted metallic lead within said classification section 5,

adjusting the number of reaction cycles by adjusting the particle velocity, reaction time and reaction temperature within said reaction section 4 to

provide the desired reduced residual content of metallic lead of said lead oxide when passing the outlet section 6,

separating said lighter particles from the classification section 5 via said outlet section 6 by introducing a second gaseous fluid via an injection section 7 into said reaction section 4 at a location downstream to said outlet section 6 to reaccelerate the particle velocity and to interfere with said introduced mixture of feedstock material and first gaseous fluid being provided to said reaction section 4 by the inlet section 2 and said gaseous fluid introduced by the by-pass section 3.

The core of the invention is to be seen in particular in that a fluidized mixture of lead containing lead oxide is conveyed in a loopreactor 1 by oxidizing the free metallic lead to a desired reacted amount. The litharge having the desired residual content of free metallic lead and a brilliant and yellow color is passed through a reaction section 4, a classification section 5 to an outlet section 6.

A further embodiment of the present invention relates to a loopreactor 1 comprising

a reaction section 4 being generally circular,

at least one inlet section 2 for essentially tangentially inserting a mixture of feedstock material and a gaseous fluid into said reaction section 4,

at least one by-pass section 3 for inserting gaseous fluid into said reaction section 4, said by-pass section 3 being located downstream to said inlet section 2 in the reaction section 4,

a classification section 5 provided downstream to said inlet section 2 and said by-pass section 3,

at least one outlet section 6, being part of said classification section 5, provided at the inner periphery of said reaction section 4 for removing particles from the centrifugal path 4a,4b of feedstock material being propelled through said loopreactor 1 and

at least one injection section 7 for introducing a second gaseous fluid into the reaction section 4 provided downstream to said outlet section 6.

## Brief Description of the Drawing

Fig. 1 is a schematic representation of the basic elements of the  
5 loopreactor 1 according to the present invention.

## Detailed Description of the Preferred Embodiments

As referred to above a serious problem in the technology of refining  
10 of litharge is to provide a constant flow of the high density material in a reactor. This problem is overcome by the present invention in particular by introducing a first fluidized mixture of lead containing lead oxide (litharge) and a first gaseous fluid into a reaction section via an inlet section 2. In order to avoid plugging in the reaction system a further stream of said first gaseous fluid is introduced into said  
15 reaction section 4 via by-pass section 3, wherein said by-pass section is located downstream to said first inlet system 2. In particular, it is preferred to introduce said first gaseous fluid transversely to the stream of the first mixture. Thus, by introducing said first gaseous fluid essentially radially inwardly or tangential to the center of the loopreactor 1 said first mixture of feedstock material and gaseous fluid  
20 is brought into a centrifugal path 4a, 4b of feedstock material. Accordingly, a constant flow of said high density material litharge is possible.

By said by-pass section 3 a partial stream of said first gaseous fluid is introduced into said stream of feedstock material and first gaseous fluid of a generally circular loopreactor at elevated temperature. By introducing said gaseous  
25 fluid the resultant mixture is moved in the reactor in a direction which is essentially tangential to the initial direction of the first introduced fluidized mixture. Due to this centrifugal acceleration of the litharge material lower weight particles and higher weight particles can be divided in a classification section 5.

The mixture of introduced feedstock material and first gaseous fluid  
30 preferably should have an inlet temperature of about 630 to about 670 °C. In the same way, within the reaction section 4, in particular before entering the classification section 5 the temperature in the loopreactor 1 should be kept at that temperature selected in the range of 600 to about 630 °C. Accordingly, the



remaining metallic lead will be practically quantitatively oxidized to the desired litharge product having a low content free metallic lead and a bright yellow color. The present invention even allows the preparation of litharge having a residual content of free metallic lead in the region of ppm. Thus, by passing the loopreactor 1 for several times the content can be reduced to traces of free metallic lead only.

The classification section 5 and the classification process in particular can be described by a curved path 4a, 4b in the reaction section 4, the curved path 4a, 4b being defined by a tractrix antifriction curvature dividing the reacted particles into heavier particles containing a partially reduced, higher content of non-reacted metallic lead and lighter particles containing a partially reduced lower content of non-reacted metallic lead within said classification section 5. Higher content of non-reacted metallic lead in a sense of the present invention has the meaning, that relative to the starting content of metallic lead, the content thereof has not been exceptionally reduced.

In order to optimize the refining process according to the present invention, the process is adjusted in a way that the lead containing litharge particles have to undergo the circular process one or several times until the desired content of lead is obtained. Once a continuous reaction has started up, the reaction may be monitored by sampling at a location close to the outlet section 6.

A further important feature of the process and the loop reactor 1 of the present invention is the injection of a second gaseous fluid via a injection section 7 into the loopreactor 1 at a location downstream to the outlet section 6 to reaccelerate the particle velocity to interfere with said introduced first mixture of feedstock material and first gaseous fluid being provided to the reactor 1 by the inlet section 2 and the by-pass section 3. This injection section 7 practically acts as a kind of pump like a water-jet pump and further divides heavier from finer particles. Thus, in a typical embodiment, air is introduced with high pressure of for example about 80 psi ( $55 \times 10^6$  pa) to about 90 psi ( $62 \times 10^6$  pa) as the second gaseous fluid. Accordingly, when introducing the feedstock material and gaseous fluid via the inlet section 2 and the first gaseous fluid provided to the reactor 1 by the by-pass section 3 with a velocity of 5000 to 20000 ft/min a continuous oxidizing reaction can be

maintained. The temperature of said second gaseous fluid introduced preferably should be within the range of about 630 °C to about 670 °C.

In a preferred embodiment, the weight ratio of the feedstock material to first gaseous fluid introduced to the reaction section by the inlet section 2 is selected in the range of about 1 : about 1 to about 1 : about 3.

For cost reasons said first gaseous fluid preferably is an oxygen containing gas. Most preferably said first gaseous fluid is air, which is preheated to the desired temperature in order to allow the injection of litharge at a temperature in the range of about 630 to about 670 °C. The volume ratio of said first gaseous fluid provided by the inlet section 2 relative to the volume of the first gaseous fluid introduced by the by-pass section 3 is of some importance. Preferably, said volume ratio is adjusted to be selected by the diameters of the tubes defining the inlet section 2 and the by-pass section 3 in the range of about 10 : 1 to about 3 : about 1.

Furthermore, the volume ratio of the combined volume of said mixture of feedstock material and first gaseous fluid provided by the inlet section 2 and first gaseous fluid introduced by the by-pass section 3 relative to the volume of the second gaseous fluid introduced by the injection section 7 is of some importance. Preferably, said volume ratio is selected in the range of about 100 : about 0.1 to about 100 : about 10.

More preferably said volume ratio is selected in a range of about 100 to about 2.

Finally, the remaining reaction time of feedstock material in the reactor 1 is adjusted in the range of about 1 to about 5 seconds. If the reaction time is adjusted as being too short, the desired reduction in content of free metallic lead will not be achieved. In case the reaction time is adjusted as being too long, the disadvantage is a worse than optimum production rate.

In order to allow a constant flow of the reaction throughout the time, the overall weight load of the reactor is adjusted to from about 25 to about 50 % by weight based on the solid particles of feedstock material. Thus, based on the heavy, high density litharge, a high dense particle stream is reacted.

After leaving the reaction section 4 of the loopreactor 1 via the outlet section 6, the litharge product has to be cooled down quickly to ambient temperature in order to avoid a further reaction to minium (red lead oxide) at a temperature of about 450°C.

5                    Although this apparatus of the present invention has been described primarily for the refining of litharge, it may also be used for such other purposes as drying, chemical reactions, coating, agglomerating or deagglomerating, and many other functions, depending on the type of gaseous fluids used, the feedstock material fed into the reactor, the velocities and pressures of the gaseous fluid as they pass into  
10                    the reactor, the angles of incidence of the nozzles relative to interior of the reactor, etc. It is to be further noted that although the reactor 1 is illustrated as being vertical, this being the preferred position, it may also be utilized in the horizontal or any other desired position.

                    The inner surface of the reactor preferably is constructed of a material  
15                    which can withstand the litharge material. In order to prevent corrosion by litharge (although it is not in liquid state in the present reactor 1), the interior hot surface of the loopreactor 1 is kept below the melting point of the litharge (888°C).

                    The residual content of metallic lead in litharge obtained by the present invention can be determined by dissolving the litharge product at room  
20                    temperature in an aqueous solution of acetic acid. An appropriate high quality of litharge is produced if the product litharge is completely dissolved without residue, providing an optically clear solution, within some seconds.

**What is Claimed is:**

1. Process for the continuous refining of litharge having a starting content of free metallic lead of about 1 to about 30 % by weight to litharge  
5 having a residual reduced content of free metallic lead of less than about 10 % by weight in a reaction section (4) of a loopreactor (1), by

introducing a first fluidized mixture of said lead containing lead oxide and a first gaseous fluid into said reaction section (4) of said loopreactor (1) via an inlet section (2),

10 further introducing said first gaseous fluid into said reaction section (4) via a by-pass section (3), said by-pass section (3) being located in the reaction section (4) of said loopreactor (1) downstream to said inlet section (2),

mixing said first fluidized mixtures with said first gaseous fluid in said reaction section (4) by propelling the resultant mixture in a direction which is  
15 essentially tangential to the initial direction of said first fluidized mixture, thereby reacting the particles of lead containing lead oxide with said first gaseous fluid,

passing said resultant, still reacting mixture through a curved path (4a,4b) in said reaction (4) section, the curved path (4a,4b) being defined by a tractrix antifriction curvature through a classification section (5) which is defined  
20 partially by a continuation of said tractrix curvature, said resultant still reacting mixture being divided into heavier particles containing a partially reduced, higher content of non-reacted metallic lead and lighter particles containing a partially reduced lower content of non-reacted metallic lead within said classification section (5),

25 adjusting the number of reaction cycles by adjusting the particle velocity, reaction time and reaction temperature within said reaction section (4) to provide the desired reduced residual content of metallic lead of said lead oxide when passing the outlet section (5),

separating said lighter particles from the classification section (5) via  
30 said outlet section (6) by introducing a second gaseous fluid via an injection section (7) into said reaction section (4) at a location downstream to said outlet section (6) to

reaccelerate the particle velocity and to interfere with said introduced first and second mixture of feedstock material and first gaseous fluid being provided to said reaction section (4) by the inlet section (2) and said first gaseous fluid introduced by the by-pass section (3).

5

2. Process according to claim 1, whereby said lead oxide is introduced into the reactor via the inlet section (2) having a starting content of metallic lead exceeding about 10 % by weight.

10

3. Process according to claim 1, whereby the weight ratio of the feedstock material to the first gaseous fluid introduced to the reaction section (4) by the inlet section (2) is selected in the range of about 1 : about 1 to about 1 : about 3.

15

4. Process according to claim 1, whereby said first gaseous fluid is an oxygen containing gas.

5. Process according to claim 1 whereby said first gaseous fluid is air.

20

6. Process according to claim 1, whereby the mixture of said feedstock material and said first gaseous fluid is introduced into the reaction section (4) at a temperature selected in the range of about 630 to about 670 °C.

25

7. Process according to claim 1, whereby the mixture of said feedstock material and said first gaseous fluid is introduced into the reaction section (4) having a velocity selected in the range of about 5,000 ft/min to about 20,000 ft/min.

8. Process according to claim 1, whereby the volume ratio of said mixture of said feedstock material and said first gaseous fluid provided by the inlet section (2) relative to the volume of said first gaseous fluid introduced by the by-pass section (3) is selected in the range of about 10 : about 1 to about 3 : about 1.

5

9. Process according to claim 1, whereby the reaction temperature in the reaction section is adjusted in the temperature range of about 600 to about 670 °C.

10

10. Process according to claim 1, whereby the volume ratio of the combined volume of said mixture of said feedstock material and said first gaseous fluid provided by the inlet section (2) and said first gaseous fluid introduced by the by-pass section (3) relative to the volume of the second gaseous fluid injected by the injection section (7) is selected in the range of about 100 : about 0,1 to about 100 : about 10.

15

11. Process according to claim 1, whereby second gaseous fluid is air at ambient temperature, introduced with a velocity selected in the range of about 5,000 ft/min to about 6,000 ft/min.

20

12. Process according to claim 1, whereby the reaction time of the feedstock material within the reactor (1) is adjusted in the range of about 1 to about 5 sec.

25

13. Process according to claim 1, whereby the overall volume load of the reactor is adjusted to about 25 to about 50 % by volume, based on the solid feedstock material.

14. A loopreactor (1) comprising  
a reaction section (4) being generally circular,  
at least one inlet section (2) for essentially tangentially introducing a  
first mixture of feedstock material and a first gaseous reactive fluid into said reaction  
5 section (4),  
at least one by-pass section (3) for inserting a second stream of said  
first gaseous reactive fluid into said reaction section (4), said by-pass section (3)  
being provided downstream to said inlet section (2),  
a classification section (5) provided downstream to said inlet section  
10 (2) and said by-pass section (3),  
at least one outlet section (6), being part of said classification section  
(5), provided at the inner periphery of said reaction section (4) for removing  
particles from the centrifugal path (4a,4b) of feedstock material being propelled  
through said loopreactor (1) and  
15 at least one injection section (7) for introducing a second gaseous  
fluid into the reaction section (4) provided downstream to said outlet section (5).
15. The loopreactor (1) according to claim 14, comprising of one  
injection section (7).
- 20
16. The loopreactor (1) according to claim 14, wherein the  
injection section (7) is provided by inclined nozzles, connected to a source of  
gaseous fluid under pressure, lead into said reaction section (4).
- 25
17. The loopreactor (1) according to claim 14, comprising one  
inlet section (2).

18. The loopreactor (1) according to claim 14, comprising one by-pass section (3).

19. The loopreactor (1) according to claim 14, wherein said by-pass section (3) is provided to essentially radially inwardly or tangentially introducing said second stream of said first gaseous fluid into said centrifugal path of feedstock material.

20. The loopreactor (1) according to claim 14, wherein the dimension of said inlet section (2) and said by-pass section (3) are selected to provide a defined ratio of the flow of the first mixture of feedstock material and first gaseous fluid provided to the reaction section (4).

21. The loopreactor (1) according to claim 14, wherein said outlet section (6) comprises an open ended tube extending transversely through said classification section (5), which is in communication with the interior of said classification section (5).



## Process and Apparatus for the Continuous Refining of Litharge

### Abstract

5

The invention relates generally to the manufacture of ortho-rhombic litharge (yellow lead oxide) and in particular to a process for the continuous refining of litharge and a loopreactor for the refining of litharge.

10

004216 59287260




FIG.1

**DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION**

As the below named inventor, I hereby declare that:

My residence, post office address and citizenship is as stated below next to my name;

I believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

**PROCESS AND APPARATUS FOR THE CONTINUOUS REFINING OF LITHARGE**

the specification of which: ☒ is attached hereto.  
☐ was filed on: \_\_\_\_\_  
as Application No.: \_\_\_\_\_  
and was amended on: \_\_\_\_\_ (if applicable).

I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above. I acknowledge the duty to disclose information which is material to patentability as defined in 37 C.F.R. § 1.56.

And I hereby authorize and request our attorneys, Brobeck, Phleger & Harrison LLP, whose address is set forth below, to insert above, the filing date and application number of said application when known.

**Prior Foreign Application(s)**

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application(s) for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

| Country | Application Number | Date of Filing<br>(day, month, year) | Date of Issue<br>(day, month, year) | Priority Claimed             |                             |
|---------|--------------------|--------------------------------------|-------------------------------------|------------------------------|-----------------------------|
|         |                    |                                      |                                     | Yes <input type="checkbox"/> | No <input type="checkbox"/> |
|         |                    |                                      |                                     | Yes <input type="checkbox"/> | No <input type="checkbox"/> |

**Prior Provisional Application(s)**

I hereby claim the benefit under Title 35, United States Code § 119(e) of any United States provisional application(s) listed below:

| Application Number | Date of Filing<br>(day, month, year) |
|--------------------|--------------------------------------|
|                    |                                      |

|  |  |
|--|--|
|  |  |
|  |  |

### Prior United States Application(s)

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s), or § 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

| Application Number | Date of Filing (day, month, year) | Status - Patented, Pending, Abandoned |
|--------------------|-----------------------------------|---------------------------------------|
|                    |                                   |                                       |
|                    |                                   |                                       |
|                    |                                   |                                       |

And I hereby appoint, both jointly and severally, as my attorneys with full power of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected herewith the following attorneys, their registration numbers being listed after their names:

Rodger L. Tate, Registration No. 27,399; Anthony W. Shaw, Registration No. 30,104; James Remenick, Registration No. 36,902; Michael J. Songer, Reg. No. 39,841; Cono A. Carrano, Registration No. 39,623; Laurence H. Posorske, Registration No. 34,698; Floyd B. Chapman, Registration No. 40,555; David J. Kulik, Registration No. 36,576; Robert A. King, Registration No. 42,738; and Trevor Q. Coddington, Registration No. 46,633.

All correspondence and telephone communications should be addressed to: Brobeck, Phleger & Harrison LLP; Intellectual Property Department; 1333 H Street, N.W.; Suite 800; Washington, DC 20005; telephone number (202) 220-6000; facsimile number (202) 220-5200, which is also the address, telephone and facsimile numbers of each of the above listed attorneys.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine and imprisonment, or both, under 18 U.S.C. § 1001, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Signature \_\_\_\_\_ Date \_\_\_\_\_  
Full Name of  
First Inventor: KLOTZ Hans G.  
(Family Name) (First Given Name) (Second Given Name)  
Citizenship: Germany  
Residence: 9419 Southmoor Avenue, #7S, Highland, Indiana 46322, USA  
Post Office  
Address: (Same as above)

Signature \_\_\_\_\_ Date \_\_\_\_\_  
Full Name of  
Second Inventor: WILKE, IV William Peter  
(Family Name) (First Given Name) (Second Given Name)  
Citizenship: USA  
Residence: 8147 Frederick Avenue, #1N, Munster, Indiana 46321, USA  
Post Office  
Address: (Same as above)

004211 6363760